

6x100 mesh

Glass Sand

MAPLE GROVE DOLOMITE

Typical Sieve Analysis

SIEVE SIZE	% RETAINED
1/4" (6.3 mm)	0.0
#4 (4.75 mm)	0.0
#6 (3.35 mm)	0.1
#8 (2.36 mm)	6.9
#10 (2.00 mm)	17.2
#12 (1.70 mm)	30.7
#16 (1.18 mm)	53.6
#20 (0.841 mm)	69.4
#30 (0.600 mm)	75.9
#50 (0.300 mm)	87.7
#100 (0.150 mm)	96.1
#200 (0.075 mm)	98.1

Moisture < 1

Average Chemical Analysis

CHEMICAL	RESULT, %
CaO	< 35.0
MgO	> 19.5
SiO ₂	< 1.0
Al ₂ O ₃	< 0.5
Fe ₂ O ₃	< 0.26

Decrepitation < 2



MGQ Aggregates, Inc. provides this information as a representative sample only. Natural minerals will vary according to the deposits from which they are mined. We will provide any serious inquiry a material sample upon request.

MGQ Aggregates

1525 County Road 42
PO Box 130
Old Fort Ohio 44861

Phone: 419 992 4235
Fax: 419 992 4545
E-mail: sthomas@mgqinc.com