

# 6x16 mesh

## MAPLE GROVE DOLOMITE

### Typical Sieve Analysis

SIEVE SIZE	% RETAINED
1/4" (6.3 mm)	0.0
#4 (4.75 mm)	0.0
#6 (3.35 mm)	0.1
#8 (2.36 mm)	26.4
#10 (2.00 mm)	33.3
#12 (1.70 mm)	60.6
#16 (1.18 mm)	90.2
#20 (0.841 mm)	93.5
#30 (0.600 mm)	96.4
#50 (0.300 mm)	98.7
#100 (0.150 mm)	99.1
#200 (0.075 mm)	99.1

Moisture < 1

### Average Chemical Analysis

CHEMICAL	RESULT, %
CaO	< 35.0
MgO	> 19.5
SiO <sub>2</sub>	< 1.0
Al <sub>2</sub> O <sub>3</sub>	< 0.5
Fe <sub>2</sub> O <sub>3</sub>	< 0.26

Decrepitation < 2

### MGQ Aggregates

1525 County Road 42  
PO Box 130  
Old Fort Ohio 44861

Phone: 419 992 4235  
Fax: 419 992 4545  
E-mail: sthomas@mgqinc.com

MGQ Aggregates, Inc. provides this information as a representative sample only. Natural minerals will vary according to the deposits from which they are mined. We will provide any serious inquiry a material sample upon request.